

RESICHEM 505 DAMP SEAL

Resichem 505 Damp Seal is a solvent-free clear epoxy coating which exhibits outstanding adhesion even to poorly prepared or wet surfaces. This makes it the material of choice for priming green or damp concrete.

Typical applications

Ideal for coating concrete floors, problematic cementitious surfaces, wet or poorly prepared steel and as a laminating resin.

Characteristics

Appearance

Base:	Clear	pale
	yellow	liquid
Activator:	Amber liquid	
Mixed:	Pale	amber
	liquid	

Mixing Ratio

By weight:	1.65:1
By volume:	3:2

Density

Base:	1.15
Activator:	1.02
Mixed:	1.08

Solids content

100%

Sag Resistance

Nil at 150 microns

Coverage

Brush or roller applications:

The material should be applied in at a target thickness of 150 microns.

At 150 microns Resichem 505 Damp Seal will have a theoretical coverage rate of 6.66m² per ltr per coat.

Once cured the coated surface must have a semi gloss finish where there are signs of excessive porosity in the surface, the coating will have a dull finish. In such circumstances or where pinhole and weak spots are evident a second coat will be required.

Cure Times

The applied material should be allowed to harden for the times indicated below before being subjected to the conditions indicated:

Usable life

10°C	90 minutes
20°C	45 minutes
30°C	22.5 minutes
40°C	11 minutes

Minimum overcoating time

10°C	16 hours
20°C	8 hours
30°C	4 hours
40°C	2 hours

Maximum overcoating time

10°C	72 hours
20°C	36 hours
30°C	18 hours
40°C	9 hours

Storage life

5 years if unopened and stored in normal dry conditions (15-30°C)

Mechanical Properties

Compressive strength

Tested to ASTM D 695
629kg/cm² (8945psi)

Flexural Strength

Tested to ASTM D790
371kg/cm² (5275psi)

Hardness

Shore D to ASTM D2240
84

Pull off adhesion

Elcometer pull off adhesion tester

Dry 525psi

(cohesive in substrate)
37kg/cm²

Wet 475psi

(cohesive in substrate)
33.4 kg/cm²

Tensile Shear

Tested to ASTM D1002

On abrasive blasted mild steel with 75 micron profile
201 kg/cm² (2860 psi)

On rusted steel

167 kg/cm² (2375 psi)

Heat Resistance

Suitable for use in immersed conditions at temperatures up to 60°C. Resistant to dry heat up to 150°C dependent on load.

Quality

All Resimac Products are supplied under the scope of the company's fully documented quality system.

Warranty

Resimac warrants that the performance of the product supplied will conform to the typical descriptions quoted within this specification provided material is stored correctly and used according to the procedures detailed in the Technical Data Sheet for the material.

Health and safety

Please ensure good practice is observed at all times during the mixing and application of this product. Protective gloves and other recommended personal protective equipment must be worn during the mixing and application of this product. Before mixing and applying the material please ensure you have read and fully understood the detailed Material Safety Data Sheet

Legal Notice: The data contained within this Product Specification is furnished for information only and is believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the customer to determine the products suitability for use. Resimac accepts no liability arising out of the use of this information or the product described herein.